

Antico

AUTHENTIC RANGE



Big knots
and asperities



Wood pieces
to fill dowel holes



Black marks
and cracks



ANTICO LEGNO (Natura oil, Heavy brushed) - Sample with no contract engagement.

DESIGN PARQUET

654 rue du Chalonge, P.A. du Haut-Montigné / 35370 Torcé / FRANCE
Tél. +33 (0)2 99 49 66 66 / Fax +33 (0)2 99 49 66 67
E-mail France : commercial@designparquet.fr
E-mail Export : export@designparquet.fr

www.designparquet.com

Previous data sheet are invalid. Errors or technical informations can
be changes without notice.
Updated in : May 2025.

DATA SHEET - ANTICO

CHARACTERISTICS

Species (origin) : Oak (Europe).

Specificity : Parquet manufactured from reclaimed oak beams.

Grade : PR=PRIME - RU=RUSTIQUE - CA=CAMPAGNE - SA=SAUVAGE

Mixed grade PR/RU/CA/SA : Knots (filled or partially open) without limit of size and number, strong color variations ranging from clear brown to dark brown, worm holes, cracks and splits, discoloration, healthy sapwood tolerated limitless, wood pieces to fill dowel holes, black filled.

Support : Solid or Loft Pro : engineered wood flooring on birch plywood base.

Density : 650 kg/m³.

Finishing : Antico (Raw) / Antico Legno (Natura oil, Heavy brushed, Distressed).

Assembly : Tongue and groove (T+G).

SUPPORT	PATTERN	SIZE (MM)	LENGTH (MM)	TOP LAYER	BEVELS (IF RAW)	THERMAL RESISTANCE K/W
SOLID	VERSAILLES PANEL	23	990x990	-	-	0,13 m ²
LOFT PRO	RANDOM LENGTHS STRIPS	14 x 90	400-1200	3,5 mm	2	0,09 m ²
		14 x 135	400-1500	3,5 mm	2	0,09 m ²
		14 x 195/200*	400-1800	3,5 mm	2	0,09 m ²
	FRENCH STYLE	14 x 90 (21%)	400-1800	3,5 mm	2	0,09 m ²
		14 x 135 (32%)				
		14 x 195/200* (47%)				
	CHEVRON 45°	14 x 90	500	3,5 mm	4	0,09 m ²
	HERRINGBONE	14 x 90	500	3,5 mm	4	0,09 m ²

* width according wood supply.

COMPATIBILITIES

Compatible on low temperature hydraulic underfloor heating and cooling (according size) :

COMPATIBILITIES			GLUED LAYING		FLOATING LAYING	
SUPPORT	THICKNESS (MM)	WIDTH (MM)	HEATING UNDERFLOOR	HEATING/COOLING UNDERFLOOR	HEATING UNDERFLOOR	HEATING/COOLING UNDERFLOOR
SOLID	23	990 x 990	YES	NO	-	-
LOFT PRO	14	90 135 195/200*	YES	YES	YES	NO

* width according wood supply.

It is imperative to start the heating 4 weeks before the beginning of the laying. Heater off 48 hours before laying. Wait for 1 week and restart the heating gradually over 15-20 days. It is traditionally recommended a thermal resistance less than or equal to 0.09 m².K/W. For higher thermal resistances, a certain loss of capacity must therefore be considered. It is imperative to respect the laying rules and the manufacturer's recommendations for use, as well as the governing regulations :

- NF DTU 35.14 – Execution of hot water floors.
- The CSTB 3164 booklet – Reversible floors.

Suitable with ISO dB and Iso alu (Cf data sheet)

TYPES OF INSTALLATION

- Floating according to DTU 51-11 (Loft Pro only).
- Glued according to NF DTU 51-2.
- Nailed according to DTU 51-1 (mini thickness 20 mm).

OILED FLOOR MAINTENANCE

After installation and for maintenance, use the maintenance oil **(N+)** apply pure with a microfiber broom in a thin wiped layer. The frequency is to be determined according to the traffic. For regular maintenance, use the maintenance soap **(S)** for oiled parquet floors from Design Parquet.

- Remember to put protective pads under the legs of chairs and furniture.
- Carry out regular maintenance with a vacuum cleaner, broom, woollen cloth.
- Never wash your floor with large amounts of water.
- Do not use aggressive, abrasive, silicone or ammonia detergents.
- For persistent stains, remove with a damp sponge and neutral detergent.

INFORMATIONS

- Air humidity at the time of laying and throughout the life of the product must be between 45% and 65%.
- Fire classification :
 - Dfl-s1 (Loft pro)
 - Cfl-s1 (Solid)
- Hardness rank : C.
- Oak Monnin hardness : 4,2.

VOC EMISSIONS



*Information on the level of volatile compounds emission in inside air, that present a toxicity risk by inhalation, on a scale from A+ (very low emissions) to C (high emissions).

RANKING USE

The classification of parquet flooring is based on the class of use. The UPEC* classification does not apply to parquet flooring insofar as it can be renovated, but an equivalence can be made :

SUPPORT	THICKNESS (MM)	RANK	UPEC EQUIVALENCE
SOLID	23		U _{3s} P ₃ E ₁ C ₀
LOFT PRO	14 (3,5 mm)		U ₃ P ₂ E ₁ C ₀

* Wear, punching, water, chemistry.