

XXL EXTRA-WIDTHS STRIPS

AUTHENTIC RANGE



XXL matt varnish grade RU/CA - Sample with no contract engagement.

DESIGN PARQUET

654 rue du Chalonge, P.A. du Haut-Montigné / 35370 Torcé / FRANCE
Tél. +33 (0)2 99 49 66 66 / Fax +33 (0)2 99 49 66 67
E-mail France : commercial@designparquet.fr
E-mail Export : export@designparquet.fr

www.designparquet.com

Previous data sheet are invalid. Errors or technical informations can be changes without notice.
Updated in : May 2025.

DATA SHEET - EXTRA-WIDTHS STRIPS

CHARACTERISTICS

Species (origin) : Oak (Europe).

Grade : PR-BIS=PRIME-BIS - RU=RUSTIC - CA=CAMPAGNE - SA=SAUVAGE

Grade PR-BIS : Knots up to 15 mm, sapwoodless, slight colour variations and possible discoloration.

Grade RU : Without sapwood. Knots up to 25 mm (40 mm for planks ≥120 mm), filled or partially opened, with no limit on number. Variation of colors allowed.

Grade CA : Knots with unlimited and various sizes with wormhole limited. Pierced and crossed knots accepted. Discoloration allowed. Cracks are limited to 50 mm in end's strip. Healthy sapwood is tolerated limitless.

Grade SA : Knots (filled or partially opened) with unlimited and various sizes. Sapwood and important color variations allowed. Unlimited cracks and splits of 25 mm are accepted. Distorsions surface are authorized (slight band saw marks). Limited wormhole. Black filled. Wood rolling allowed.

Mixed grade (XXL+) : Natural oak without grade selection.

Support : Loft Pro : engineered wood flooring on birch plywood base.

Density : 650 kg/m³.

Finishing : Raw, Varnish (matt or colourless), Oil (Natura or colourless), ROC varnish.

Assembly : Tongue and groove (T+G).

SUPPORT	GRADE	SIZE (MM)	LENGTH ⁽¹⁾ (MM)	TOP LAYER ⁽²⁾	BEVELS	THERMAL RESISTANCE K/W
LOFT PRO	PR-BIS	20 x 295	1000-2400	4,0 mm	2	0,13 m²
			1800-3000	4,0 mm	2	0,13 m²
	RU	20 x 295	1000-2400	4,0 mm	2	0,13 m²
			1800-3000	4,0 mm	2	0,13 m²
	CA	20 x 295	1000-2400	4,0 mm	2	0,13 m²
			1800-3000	4,0 mm	2	0,13 m²
	SA	20 x 295	1000-2400	4,0 mm	2	0,13 m²
			1800-3000	4,0 mm	2	0,13 m²
	XXL+ MIXED	20 x 295	3000-5000 ⁽³⁾	4,0 mm	2	0,13 m²

(1) 20% lengths < to indicated dimensions.

(2) Top layer of 4,5 mm instead of 4,0 mm (or ROC varnish finish) on request, to achieve the higher ranking use.

(3) For the XXL+ flooring, we can only deliver to a warehouse to unload 5-meter strips with a suitable forklift. Please note, no delivery to the construction site.

COMPATIBILITIES

Compatible on low temperature hydraulic underfloor heating and cooling (according size) :

COMPATIBILITIES			GLUED LAYING		FLOATING LAYING	
SUPPORT	THICKNESS (MM)	WIDTH (MM)	HEATING UNDERFLOOR	HEATING/COOLING UNDERFLOOR	HEATING UNDERFLOOR	HEATING/COOLING UNDERFLOOR
LOFT PRO	20	295	YES	NO	NO	NO

It is imperative to start the heating 4 weeks before the beginning of the laying.
 Heater off 48 hours before laying. Wait for 1 week and restart the heating gradually over 15-20 days. It is traditionally recommended a thermal resistance less than or equal to 0.09 m².K/W.
 For higher thermal resistances, a certain loss of capacity must therefore be considered.
 It is imperative to respect the laying rules and the manufacturer's recommendations for use, as well as the governing regulations :

- NF DTU 35.14 – Execution of hot water floors.
- The CSTB 3164 booklet – Reversible floors.

Suitable with ISO dB and Iso alu (Cf data sheet)

TYPES OF INSTALLATION

- Floating according to DTU 51-11.
- Glued according to NF DTU 51-2.
- Nailed according to DTU 51-1.

FLOOR MAINTENANCE

After installation, it is imperative to apply the following products to the parquet floor, depending on its finish :

FINISHING	DAILY CLEANING	AFTER INSTALLATION AND REGULAR MAINTENANCE	
VARNISH	CLEANER	RENOVATOR MATT	
NATURA OIL	NATURAL SOAP	MAINTENANCE OIL	
COLOURLESS OIL	NATURAL SOAP	MAINTENANCE OIL	

- Remember to put protective pads under the legs of chairs and furniture.
- Carry out regular maintenance with a vacuum cleaner, broom, woollen cloth.
- Never wash your floor with large amounts of water.
- Do not use aggressive, abrasive, silicone or ammonia detergents.
- For persistent stains, remove with a damp sponge and neutral detergent.

INFORMATIONS

- Air humidity at the time of laying and throughout the life of the product must be between 45% and 65%.
- Fire classification :
 - Dfl-s1 (Loft pro)
- Hardness rank : C.
- Oak Monnin hardness : 4,2.

VOC EMISSIONS



*Information on the level of volatile compounds emission in inside air, that present a toxicity risk by inhalation, on a scale from A+ (very low emissions) to C (high emissions).

RANKING USE

The classification of parquet flooring is based on the class of use. The UPEC* classification does not apply to parquet flooring insofar as it can be renovated, but an equivalence can be made :

SUPPORT	SECTION	CLASSE	ÉQUIVALENCE UPEC
LOFT PRO	20 (4,0)		U ₃ P ₂ E ₁ C ₀
	20 (4,5)		U _{3s} P ₃ E ₁ C ₀

** Wear, punching, water, chemistry.*