

Havane

DESIGN DECO RANGE



Sample with no contract engagement.

DESIGN PARQUET

654 rue du Chalonge, P.A. du Haut-Montigné / 35370 Torcé / FRANCE

Tél. +33 (0)2 99 49 66 66 / Fax +33 (0)2 99 49 66 67

E-mail France : commercial@designparquet.fr

E-mail Export : export@designparquet.fr

www.designparquet.com

Previous data sheet are invalid. Errors or technical informations can be changes without notice.

Updated in : August 2026.

DATA SHEET - HAVANE

CHARACTERISTICS

Species (origin) : Oak (Europe).

Grade : PR=PRIME - RU=RUSTIC - CA=CAMPAGNE

Mixed grade PR/RU : Small knots up to 25 mm for ≤ 119 mm width planks, and up to 40 mm for wider planks (≥ 120 mm), no limit on the knots amount. Colour variations and discolouration allowed. Filled or partially opened knots.

Mixed grade RU/CA : Parquet floor with knots (filled or partially opened) with unlimited and various sizes. Sapwood and colour variations allowed.

PR : Small knots up to 10 mm, sapwoodless, slight colour variations.

RU : No sapwood. Knots up to 25 mm for ≤ 119 mm width planks, and up to 40 mm for wider planks (≥ 120 mm), no limit on the knots amount. Colour variations and discolouration allowed.

CA : Limitless filled and partially open knots in size and number. Limited wormholes. Pierced and crossed knots allowed. Colour variations, discolourations, cracks and splits allowed. Limited splits in end's strips. Sapwood allowed.

Support : Loft Pro : engineered wood flooring on birch plywood base.

Density : 650 kg/m³.

Mass processing : Smocked.

Finishing : Colourless oil.

Assembly : Tongue and groove (T+G).

Possible appearance : Distressed (no bevels).

Specificity : Thanks to the smocking process, each floorboard develops distinct color variations, from warm, intense tones to darker, mysterious hues. These living, evolving colors will continue to change subtly over time.

SUPPORT	PATTERN	SIZE (MM)	LENGTH (MM)	TOP LAYER	BEVELS	THERMAL RESISTANCE K/W
LOFT PRO	RANDOM LENGTHS STRIPS	12 x 145	1000-2000*	3,2 mm	2	0,08 m ²
		15 x 180	1000-2000*	3,5 mm	2	0,09 m ²
		15 x 220	1000-2000*	3,5 mm	2	0,09 m ²
	CHEVRON 45°	15 x 86	500	3,5 mm	4	0,09 m ²
	HERRINGBONE	15 x 86	500	3,5 mm	4	0,09 m ²

* 20% lengths < to 1000 mm.

COMPATIBILITIES

Compatible on low temperature hydraulic underfloor heating and cooling (according size) :

COMPATIBILITIES			GLUED LAYING		FLOATING LAYING	
SUPPORT	THICKNESS (MM)	WIDTH (MM)	HEATING UNDERFLOOR	HEATING/COOLING UNDERFLOOR	HEATING UNDERFLOOR	HEATING/COOLING UNDERFLOOR
LOFT PRO	12	145	YES	YES	YES	NO
	15	86/180/220	YES	YES	YES	NO

It is imperative to start the heating 4 weeks before the beginning of the laying.

Heater off 48 hours before laying. Wait for 1 week and restart the heating gradually over 15-20 days. It is traditionally recommended a thermal resistance less than or equal to 0.09 m².K/W.

For higher thermal resistances, a certain loss of capacity must therefore be considered.

It is imperative to respect the laying rules and the manufacturer's recommendations for use, as well as the governing regulations :

- NF DTU 35.14 – Execution of hot water floors.
- The CSTB 3164 booklet – Reversible floors.

Suitable with ISO dB and Iso alu (Cf data sheet).

TYPE OF INSTALLATION

- Floating according to DTU 51-11.
- Glued according to NF DTU 51-2.

OILED FLOOR MAINTENANCE


After installation and for maintenance, use the maintenance oil (H+) apply pure with a microfiber broom in a thin wiped layer. The frequency is to be determined according to the traffic. For regular maintenance, use the maintenance soap (S+) for oiled parquet floors from Design Parquet.

- Remember to put protective pads under the legs of chairs and furniture.
- Carry out regular maintenance with a vacuum cleaner, broom, woollen cloth.
- Never wash your floor with large amounts of water.
- Do not use aggressive, abrasive, silicone or ammonia detergents.
- For persistent stains, remove with a damp sponge and neutral detergent.

INFORMATIONS

- Air humidity at the time of laying and throughout the life of the product must be between 40% and 60%.
- Fire classification :
 - Dfl-s1 (according to NF EN 14342)
- Hardness rank : C.
- Oak Monnin hardness : 4,2.

VOC EMISSIONS



*Information on the level of volatile compounds emission in inside air, that present a toxicity risk by inhalation, on a scale from A+ (very low emissions) to C (high emissions).

RANKING USE

The classification of parquet flooring is based on the class of use. The UPEC* classification does not apply to parquet flooring insofar as it can be renovated, but an equivalence can be made :

SUPPORT	THICKNESS (MM)	RANK	UPEC EQUIVALENCE
LOFT PRO	12		U ₃ P ₃ E ₁ C ₀
	15		U ₃ P ₃ E ₁ C ₀

* Wear, punching, water, chemistry.