

Jatoba

EXOTIC RANGE



Satin
varnish



Miscellaneous
browns



Singularities



Sample with no contract engagement.

DATA SHEET - JATOBA

CHARACTERISTICS

Species (origin) : Jatoba (South of America).

Description : Beige, pink brown to red brown, sometimes veined (variation of color).

Support : Solid or Loft Pro : engineered wood flooring on plywood base.

Density : 940 kg/m³.

Finishing : Raw, Satin varnish, Natura oil or ROC Satin varnish.

Assembly : Tongue and groove (T+G), Lamparquet (size 10 x 60).

Particularity : Wood is a natural material that evolves over time. Under the effect of sunlight, the color of your floor will age, a process that stabilizes after a few months of exposure.

SUPPORT	SIZE (MM)	LENGTH (MM)	TOP LAYER	BEVELS	THERMAL RESISTANCE K/W
SOLID	10 x 60 (lamparquet)	300	-	NO	0,04 m ²
	14 x 90	300-1200	-	NO or 4	0,06 m ²
	14 x 120/130 ⁽¹⁾	300-1200	-	NO	0,06 m ²
	14 x 118	400-1200	-	4	0,06 m ²
	19 x 140 ⁽²⁾	600-1200	-	NO	0,09 m ²
	20 x 130/140 ⁽¹⁾	400-1800	-	NO or 4	0,09 m ²
LOFT PRO	15 x 140	500-1800	3,5 mm	2	0,07 m ²

(1) According to wood supply

(2) limited stock

TYPE OF INSTALLATION

- Floating according to DTU 51-11 (Loft Pro only).
- Glued according to NF DTU 51-2.
- Nailed according to DTU 51-1 (minimum thickness 20 mm).

COMPATIBILITIES

Not compatible on low temperature hydraulic underfloor heating and cooling.

Suitable with ISO dB and Iso alu (Cf data sheet).

FLOOR MAINTENANCE

After installation, it is imperative to apply the following products to the parquet floor, depending on its Design Parquet finish :


FINISHING	DAILY CLEANING	REGULAR MAINTENANCE AND AFTER INSTALLATION
VARNISH	CLEANER L+	RENOVATOR MATT R+
NATURA OIL	NATURAL SOAP S+	MAINTENANCE OIL N+

- Remember to put protective pads under the legs of chairs and furniture.
- Carry out regular maintenance with a vacuum cleaner, broom, woollen cloth.
- Never wash your floor with large amounts of water.
- Do not use aggressive, abrasive, silicone or ammonia detergents.
- For persistent stains, remove with a damp sponge and neutral detergent.

INFORMATIONS

- Air humidity at the time of laying and throughout the life of the product must be between 40% and 60%.
- Fire classification :
 - Dfl-s1 (Loft pro)
 - Cfl-s1 (solid)
- Hardness rank : D.
- Jatoba Monnin hardness : 10,5.

VOC EMISSIONS



*Information on the level of volatile compounds emission in inside air, that present a toxicity risk by inhalation, on a scale from A+ (very low emissions) to C (high emissions).

RANKING USE

The classification of parquet flooring is based on the class of use. The UPEC* classification does not apply to parquet flooring insofar as it can be renovated, but an equivalence can be made :

SUPPORT	THICKNESS (MM)	RANK	UPEC EQUIVALENCE
SOLID	10 (lamparquet)		U _{3S} P ₃ E ₁ C ₀
	14		U _{3S} P ₃ E ₁ C ₀
	19		U _{3S} P ₃ E ₁ C ₀
	20		U _{3S} P ₃ E ₁ C ₀
LOFT PRO	15		U _{3S} P ₃ E ₁ C ₀

* Wear, punching, water, chemistry.