

# Industrial flooring

## Ash in strips

MOSAIC RANGE



*Sample with no contract engagement.*

---

### DESIGN PARQUET

654 rue du Chalonge, P.A. du Haut-Montigné / 35370 Torcé / FRANCE  
Tél. +33 (0)2 99 49 66 66 / Fax +33 (0)2 99 49 66 67  
E-mail France : [commercial@designparquet.fr](mailto:commercial@designparquet.fr)  
E-mail Export : [export@designparquet.fr](mailto:export@designparquet.fr)

[www.designparquet.com](http://www.designparquet.com)

Previous data sheet are invalid. Errors or technical informations can  
be changes without notice.  
Updated in : January 2026.

# DATA SHEET - INDSTR. FLOORING MOSAIC

## CHARACTERISTICS

**Species (origin) :** Ash (Europe) - *industrial flooring, according to the standard EN14761.*


**Industrial Grade :** Parquet Floor with significant colour variation and unlimited healthy sapwood.

**Support :** Solid.

**Density :** 680 kg/m<sup>3</sup>.

**Finishing :** Unfinished (filling necessary during the process of installation).

**Note :** Industrial flooring is a product manufactured from factory-rejects. Prices and sizes as well as stock are given on an indication basis. We reserve the right to change the above information depending on the wood supply.



SUPPORT	THICKNESS (MM)	WIDTH (MM)	LENGTH (MM)	BEVELS	THERMAL RESISTANCE K/W
SOLID	22	8	160	NO	0,13 m <sup>2</sup>

## TYPES OF INSTALLATION

- Glued according to NF DTU 51-2.

## COMPATIBILITIES

Not compatible on low temperature hydraulic underfloor heating and cooling.

Suitable with ISO dB and Iso alu (Cf data sheet).

## MAINTENANCE FLOOR


After finish :

- Remember to put protective pads under the legs of chairs and furniture.
- Carry out regular maintenance with a vacuum cleaner, broom, woollen cloth.
- Never wash your floor with large amounts of water.
- Do not use aggressive, abrasive, silicone or ammonia detergents.
- For persistent stains, remove with a damp sponge and neutral detergent.

## INFORMATIONS

- Air humidity at the time of laying and throughout the life of the product must be between 40% and 60%.
- Fire classification :
  - Cfl-s1 (Solid)
- Hardness rank : C.
- Ash Monnin hardness : 5,1.

## VOC EMISSIONS



\*Information on the level of volatile compounds emission in inside air, that present a toxicity risk by inhalation, on a scale from A+ (very low emissions) to C (high emissions).

## RANKING USE

The classification of parquet flooring is based on the class of use. The UPEC\* classification does not apply to parquet flooring insofar as it can be renovated, but an equivalence can be made :

SUPPORT	THICKNESS (MM)	RANK	UPEC EQUIVALENCE
SOLID	22		U3S P3 E1 Co

\*Usure, Poinçonnage, Eau, Chimie.