

CONFORT OAK

NATURAL OAK RANGE

Light sapwood,
knots until 15mm



Confort oak, matt varnish. Sample with no contract engagement.

DESIGN PARQUET

654 rue du Chalonge, P.A. du Haut-Montigné / 35370 Torcé / FRANCE

Tél. +33 (0)2 99 49 66 66 / Fax +33 (0)2 99 49 66 67

E-mail France : commercial@designparquet.fr

E-mail Export : export@designparquet.fr

www.designparquet.com

Previous data sheets are invalid. Errors or technical informations
can be changes without notice.

Updated in : August 2026.

DATA SHEET - CONFORT OAK

CHARACTERISTICS

- Species (origin) :** Oak (Europe).
- Grade :** CONFORT : Knots up to 15 mm, light sapwood, colour variations and discoloration possible. Grade for widths between 130 and 145 mm.
- Support :** Solid
- Density :** 650 kg/m³.
- Finishing :** Raw, Varnished (matt or colourless or satin), Oiled (Natura or colourless), or matt ROC Varnish.
- Assembly :** Tongue and groove (T+G).
- Possible appearance :** Distressed (no bevels), brushed, heavy brushed, very heavy brushed, sawn marks.
- Pattern :** Random lengths strips (others laying on request).

SUPPORT	SIZE (MM) ⁽¹⁾	TOP LAYER	BEVELS	THERMAL RESISTANCE K/W
SOLID	14 x 130	6	NO ou 4	0,09 m²
LOFT PRO	12 x 145	3,	2	0,08 m²

(1) Refer to the pricelist to know all length available according to the size.

TYPES OF INSTALLATION

- Glued according to NF DTU 51-2.
- Floating according to NF DTU 51.11

COMPATIBILITIES

Compatible on low temperature hydraulic underfloor heating and cooling (according size) :

COMPATIBILITIES			GLUED LAYING		FLOATING LAYING	
SUPPORT	THICKNESS (MM)	WIDTH (MM)	HEATING UNDERFLOOR	COOLING UNDERFLOOR	HEATING UNDERFLOOR	COOLING UNDERFLOOR
SOLID	14	130	OUI	OUI	-	-
LOFT PRO	12	145	OUI	OUI	OUI	NON

- It is imperative to start the heating 4 weeks before the beginning of the laying.
- Heater off 48 hours before laying. Wait for 1 week and restart the heating gradually over 15-20 days. It is traditionally recommended a thermal resistance less than or equal to 0.09 m².K/W.
- For higher thermal resistances, a certain loss of capacity must therefore be considered.
- It is imperative to respect the laying rules and the manufacturer’s recommendations for use, as well as the governing regulations :
- NF DTU 35.14 – Execution of hot water floors.
 - The CSTB 3164 booklet – Reversible floors.
- Suitable with ISO dB and Iso alu (Cf data sheet).

FLOOR MAINTENANCE

After installation, it is imperative to apply the following products to the parquet floor, depending on its finish :

FINISHING	DAILY CLEANING	AFTER INSTALLATION AND REGULAR MAINTENANCE	
VARNISH	CLEANER	RENOVATOR MATT	
NATURA OIL	NATURAL SOAP	MAINTENANCE OIL	
COLOURLESS OIL	NATURAL SOAP	MAINTENANCE OIL	

- Remember to put protective pads under the legs of chairs and furniture.
- Carry out regular maintenance with a vacuum cleaner, broom, woollen cloth.
- Never wash your floor with large amounts of water.
- Do not use aggressive, abrasive, silicone or ammonia detergents.
- For persistent stains, remove with a damp sponge and neutral detergent.

INFORMATIONS

- Air humidity at the time of laying and throughout the life of the product must be between 40% and 60%.
- Fire classification :
 - Cfl-s1 for solid
 - Dfl-S1 for Loft pro
- Hardness rank : C.
- Oak Monnin hardness : 4,2.

VOC EMISSIONS



*Information on the level of volatile compounds emission in inside air, that present a toxicity risk by inhalation, on a scale from A+ (very low emissions) to C (high emissions).

RANKING USE

The classification of parquet flooring is based on the class of use. The UPEC* classification does not apply to parquet flooring insofar as it can be renovated, but an equivalence can be made :

SUPPORT	THICKNESS (MM)	RANK	UPEC EQUIVALENCE
SOLID	14		U _{3S} P ₃ E ₁ C ₀
LOFT PRO	12 (3,2 mm)		U ₃ P ₃ E ₁ C ₀

* Wear, punching, water, chemistry.