

# Suisse

PANELS RANGE



*Sample with no contract engagement.*

---

## DESIGN PARQUET

654 rue du Chalonge, P.A. du Haut-Montigné / 35370 Torcé / FRANCE  
Tél. +33 (0)2 99 49 66 66 / Fax +33 (0)2 99 49 66 67  
E-mail France : [commercial@designparquet.fr](mailto:commercial@designparquet.fr)  
E-mail Export : [export@designparquet.fr](mailto:export@designparquet.fr)

[www.designparquet.com](http://www.designparquet.com)

Previous data sheet are invalid. Errors or technical informations can  
be changes without notice.  
Updated in : January 2026.

# DATA SHEET - SUISSE PANELS

## CHARACTERISTICS

**Species (origin) :** Oak (Europe).

**Grade :** PR-BIS=PRIME-BIS - RU=RUSTIC - CA=CAMPAGNE

Grade PR-BIS : Knots up to 15 mm, sapwoodless, slight colour variations and possible discoloration.

Mixed grade RU/CA : Parquet floor with knots (filled or partially opened) with unlimited and various sizes. Sapwood and color variations allowed.

**Support** : Loft pro : engineered wood flooring on birch plywood base.


**Density** : 650 kg/m<sup>3</sup>.

**Finishing** : Raw (Varnished or Oiled on request).

**Assembly** : Tongue and groove (T+G).

**Possible appearance** : Natural (Brushed, Heavy brushed, Distressed or Sawn marks on request).

**Particularity** : A functional gap is built between the panels to absorb the natural dimensional variations of oak.



| SUPPORT  | THICKNESS (MM) | SIZE (MM)   | TOP LAYER | BEVELS | THERMAL RESISTANCE K/W |
|----------|----------------|-------------|-----------|--------|------------------------|
| LOFT PRO | 15             | 1000 x 1000 | 4,0 mm    | NO     | 0,09 m <sup>2</sup>    |

## TYPES OF INSTALLATION

- Glued according to NF DTU 51-2.

## COMPATIBILITIES

Compatible on low temperature hydraulic underfloor heating and cooling (according size) :

| COMPATIBILITIES |                |           | GLUED LAYING       |                            |
|-----------------|----------------|-----------|--------------------|----------------------------|
| SUPPORT         | THICKNESS (MM) | SIDE (MM) | HEATING UNDERFLOOR | HEATING/COOLING UNDERFLOOR |
| LOFT PRO        | 15             | 1000      | YES                | YES                        |

It is imperative to start the heating 4 weeks before the beginning of the laying.

Heater off 48 hours before laying. Wait for 1 week and restart the heating gradually over 15-20 days. It is traditionally recommended a thermal resistance less than or equal to 0.09 m<sup>2</sup>.K/W. For higher thermal resistances, a certain loss of capacity must therefore be considered.

It is imperative to respect the laying rules and the manufacturer's recommendations for use, as well as the governing regulations :

- NF DTU 35.14 – Execution of hot water floors.
- The CSTB 3164 booklet – Reversible floors.

Suitable with ISO dB and Iso alu (Cf data sheet).

## FLOOR MAINTENANCE

*(If Design Parquet finish requested)*

After installation, it is imperative to apply the following products to the parquet floor, depending on its finish :

| FINISHING      | DAILY CLEANING | REGULAR MAINTENANCE AND AFTER INSTALLATION |
|----------------|----------------|--|
| VARNISH        | CLEANER        | RENOVATOR MATT (L+)                        |
| NATURA OIL     | NATURAL SOAP   | MAINTENANCE OIL (N+)                       |
| COLOURLESS OIL | NATURAL SOAP   | MAINTENANCE OIL (H+)                       |

- Remember to put protective pads under the legs of chairs and furniture.
- Carry out regular maintenance with a vacuum cleaner, broom, woollen cloth.
- Never wash your floor with large amounts of water.
- Do not use aggressive, abrasive, silicone or ammonia detergents.
- For persistent stains, remove with a damp sponge and neutral detergent.

## INFORMATIONS

- Air humidity at the time of laying and throughout the life of the product must be between 40% and 60%.
- Fire classification :
  - Dfl-s1 (Loft pro)
- Hardness rank : C.
- Oak Monnin hardness : 4,2.

## VOC EMISSIONS



\*Information on the level of volatile compounds emission in inside air, that present a toxicity risk by inhalation, on a scale from A+ (very low emissions) to C (high emissions).

## RANKING USE

The classification of parquet flooring is based on the class of use. The UPEC\* classification does not apply to parquet flooring insofar as it can be renovated, but an equivalence can be made :

| SUPPORT  | THICKNESS (MM) | RANK | UPEC EQUIVALENCE  |
|----------|----------------|------|---|
| LOFT PRO | 15             |      | U <sub>3</sub> P <sub>3</sub> E <sub>1</sub> C <sub>0</sub> |

\* Wear, punching, water, chemistry.